

Top side: Smooth gloss (SG)





Quality: PU80A Order No.: FBFJ150X32OG

FDA EC

GENERAL BELT INFORMATION						
Material type	Polyurethane	Belt design	monolithic			
Total belt thickness	3,2 mm	Weight	3,84 kg/m²			
Minimum pulley diameter	30 mm	Temperature	-20°C+60°C			
Recommended pretension	15%	Maximum production width	150 mm			
Pull force at 1% elongation (static)	0,94 N/mm	Maximum usable width	140 mm			
		Chemical resistance	upon request			
Pull force at 1% elongation (relaxed)	0,8 N/mm					

EC

BELT SPECIFICATIONS	TOP SIDE	BOTTOM SIDE
Approx. material hardness (Shore)	84° Shore A	84° Shore A
Coefficient of friction µ Steel	0,65	0,65
Color	orange	orange
Belt thickness	n/a	n/a
Surface	Smooth gloss (SG)	Smooth gloss (SG)
Characteristics	FDA (Food and Drug Administration)	FDA (Food and Drug Administration)

CON	IFORMITY
REA	CH EG 1907/2006 in the current versions
EG 1	1935/2004 in the current versions
EG 1	10/2011 in the current versions
FDA	(Food and Drug Administration)
EG 1	1935/2004 in the current versions 10/2011 in the current versions

RECOMMENDED END CONNECTION & WELDING PARAMETERS						
Finger joint		Butt welding (heating sword)				
Heating plate temperature	160 °C	Heating paddle temperature	260°C ±10°C			
Pressure	0,5 bar					
Heating time	120 sek.					

The above information is the result of in-house quality testing. It does not constitute a warranty of properties and, in particular, does not contain statements about the suitability of the product for specific purposes, nor can any claims be derived from it against us. The information does not release the buyer, in particular, from his obligation to perform incoming inspection.

Subject to change without notice - 11/2024



MATERIAL CHARACTERISTICS

BEHAbelt conveyor belts additionally offer very useful special features that make them suitable for even the most demanding conveyor belt applications.



FDA/EC compliance for direct food contact.



Metal and X-ray detectable conveyor belts for maximum food safety. These products are part of the PUsafe series.



Hydrolysis-resistant conveyor belts for use in warm, humid, and wet environments.



Specially protected against UV-C radiation.



Use of raw materials of non-animal origin.



Friction driven conveyor belts for roller drives.



Antistatic dissipative conveyor belts with excellent mechanical properties.



The microbe-resistant conveyor belts do not provide a breeding ground for microorganisms.



Unique surface finish that offers optimal release properties and excellent cleanability due to its rounded structure.



The two-component production allows the combination of different material hardnesses, properties, and colors.




Heavy-duty flame retardant according to ISO 340.



Form-locking conveyor belts for gear drives.

DELIVERY PROGRAM

Supplementary product solutions as well as welding and joining technology.



made of PU and TPE



Monolithic conveyor belts Weldable belts made of PU Welding/joining technology and TPF



for PU and TPE



PU coatings for toothed and V-belts



Belt accessories made of PU