

Top side: Smooth matt (SM)

Bottom side: Fabric impression (FI)

Quality: **PU95A**

Order No.: FBFL750X30WA





GENERAL BELT INFORMATION

aterial type	Polyurethane	Belt design	monolithic			
otal belt thickness	3 mm	Weight	3,6 kg/m ²			
inimum pulley diameter	50 mm	Temperature	-30°+60°C			
ecommended pretension	0.53%	Maximum production width	750 mm			
Pull force at 1% elongation (static)	1,5 N/mm	Maximum usable width	730 mm			
		Chemical resistance	upon request			
ull force at 1% elongation elaxed)	1,28 N/mm					
btal belt thickness inimum pulley diameter ecommended pretension ull force at 1% elongation tatic) ull force at 1% elongation	50 mm 0.53% 1,5 N/mm	Temperature Maximum production width Maximum usable width	-30°+60°C 750 mm 730 mm			

BELT SPECIFICATIONS	TOP SIDE	BOTTOM SIDE		
Approx. material hardness (Shore)	95° Shore A	95° Shore A		
Coefficient of friction $\boldsymbol{\mu}$ Steel	0,4	0,3		
Color	white	white		
Belt thickness	n/a	n/a		
Surface	Smooth matt (SM)	Fabric impression (FI)		
Characteristics	Hydrolysis resistance	Hydrolysis resistance		
	microbial resistant	microbial resistant		
	MicroClean	Cold-flexible		
	Cold-flexible	FDA (Food and Drug Administration)		
	FDA (Food and Drug Administration)			

CONFORMITY	RECOMMENDED END CONNECTION & WELDING			
REACH EC 1907/2006 in the current versions	PARAMETERS			
EC 1935/2004 in the current versions	Finger joint		Butt welding (heating sword)	
FDA (Food and Drug Administration)	Heating plate temperature	175 °C	Heating paddle temperature	260°C ±10°C
	Pressure			
	Heating time	120 sek.		

The above information is the result of in-house quality testing. It does not constitute a warranty of properties and, in particular, does not contain statements about the suitability of the product for specific purposes, nor can any claims be derived from it against us. The information does not release the buyer, in particular, from his obligation to perform incoming inspection.

Subject to change without notice - 04/2025



MATERIAL CHARACTERISTICS

BEHAbelt conveyor belts additionally offer very useful special features that make them suitable for even the most demanding conveyor belt applications.



FDA/EC compliance for direct food contact.



Metal and X-ray detectable conveyor belts for maximum food safety. These products are part of the PUsafe series.



Hydrolysis-resistant conveyor belts for use in warm, humid, and wet environments.



Specially protected against UV-C radiation.



Use of raw materials of non-animal origin.



Friction driven conveyor belts for roller drives.



Antistatic dissipative conveyor belts with excellent mechanical properties.



The microbe-resistant conveyor belts do not provide a breeding ground for microorganisms.



Unique surface finish that offers optimal release properties and excellent cleanability due to its rounded structure.



The two-component production allows the combination of different material hardnesses, properties, and colors.



Heavy-duty flame retardant according to ISO 340.



Form-locking conveyor belts for gear drives.

DELIVERY PROGRAM

Supplementary product solutions as well as welding and joining technology.



made of PU and TPE



Monolithic conveyor belts Weldable belts made of PU Welding/joining technology for PU and TPE and TPE

PU coatings for toothed and V-belts



Belt accessories made of PU