

Round belts

**PU80A SAFE capri blue smooth**



approx. 84° Shore A

Recommended Pretension 3...6%

Coeff. of friction  $\mu$  steel approx. 0,65

Coeff. of friction  $\mu$  PE approx. 0,35

Coeff. of friction  $\mu$  HDPE approx. 0,3

FDA/EC compliant

Article no.	Diameter $\varnothing$		Cross section $\text{cm}^2$	approx. weight $\text{kg}/100\text{m}$	Standard roll		Recommended min. pulley $\varnothing$		Fmax/belt (standard)	
	mm	inch			m	ft	mm	inch	kg	lbs
FBRJ020LGM	2	5/64	0.032	0,5	200	656	15	0,6	0,6	1,3
FBRJ030LGM	3	1/8	0.071	0,9	200	656	25	1	1,6	3,5
FBRJ032LGM	3,2	1/8	0.071	0,9	30	100	25	1	1,7	3,7
FBRJ040LGM	4	5/32	0.126	1,6	200	656	30	1,2	2,9	6,4
FBRJ048LGM	4,8	3/16	0.181	2,2	30	100	40	1,6	4	8,8
FBRJ050LGM	5	1/5	0.197	2,4	100	328	45	1,8	5,6	12,3
FBRJ060LGM	6	7/32	0.283	3,4	100	328	55	2,2	6,4	14,1
FBRJ063LGM	6,3	1/4	0.310	3,8	30	100	60	2,4	6,9	15,2
FBRJ070LGM	7	9/32	0.385	4,7	100	328	65	2,6	9,3	20,5
FBRJ079LGM	7,9	5/16	0.500	6	30	100	75	3	12	26,4
FBRJ080LGM	8	5/16	0.500	6	100	328	75	3	12	26,4
FBRJ095LGM	9,5	3/8	0.710	8,5	30	100	90	3,5	17	37,4
FBRJ100LGM	10	7/16	0.785	9,4	50	164	95	3,7	18,9	41,6
FBRJ120LGM	12	15/32	1.130	13,5	50	164	110	4,3	27,2	59,9
FBRJ125LGM	12,5	1/2	1.230	14,8	30	100	115	4,5	29,4	64,7
FBRJ143LGM	14,3	9/16	1.605	21	30	100	130	5,1	37	81,4
FBRJ150LGM	15	19/32	1.770	21,5	50	164	140	5,5	42,4	93,3

**Characteristics**



**Metal detectable**



**X-ray detectable**



**FDA (Food and Drug Administration)**

FDA/EC conformity for direct food contact

The above information is the result of in-house quality testing. They do not contain any guarantee of properties and in particular do not contain any statements about the suitability of the product for specific purposes, so that no claims against us can be derived from them. In particular, the information does not release the purchaser from his obligation to inspect incoming goods.

Subject to change without notice - 08/2024