

Round belts

PU85A ultramarine blue smooth, Reinforced Glass fibre PU, weldable



approx. 88° Shore A

Recommended Pretension 0.5...2%

Coeff. of friction μ steel approx. 0,6

Coeff. of friction μ PE approx. 0,35

Coeff. of friction μ HDPE approx. 0,3

Article no.	Diameter \varnothing		Cross section cm ²	approx. weight kg/100m	Standard roll		Recommended min. pulley \varnothing		Fmax/belt (standard)		Fmax/belt (overlap)	
	mm	inch			m	ft	mm	inch	kg	lbs	kg	lbs
FBZRP85A080	8	5/16	0,5	6	100	328	85	3,4	19,8	43,5		
FBZRP85A095	9,5	3/8	0,71	8,5	100	328	100	4	28,1	61,9		
FBZRP85A100	10	7/16	0,785	9,4	50	164	105	4,2	31	68,2		
FBZRP85A120	12	15/32	1.130	13,5	50	164	125	5	44,7	98,3		
FBZRP85A125	12,5	1/2	1,23	14,8	50	164	130	5,2	48,6	107		
FBZRP85A143	14,3	9/16	1.605	21	50	164	150	6	63,4	139,4		
FBZRP85A150	15	19/32	1,77	21,5	50	164	155	6,2	69,9	153,8		

Characteristics



with reinforcement
 for applications that require a higher pull force.

The above information is the result of in-house quality testing. They do not contain any guarantee of properties and in particular do not contain any statements about the suitability of the product for specific purposes, so that no claims against us can be derived from them. In particular, the information does not release the purchaser from his obligation to inspect incoming goods.

Subject to change without notice - 04/2025