

Special profiles

PU95A beige smooth



Article no.	Dimensions	Cross section	approx. weight	Standard roll		Recommended min. pulley Øø		Fmax/belt (standard)	
	mm	cm²	kg/100m	m	ft	mm	inch	kg	lbs
FBSM12X8BG	12x8	0,67	7,9	50	164	120	4,7	32,7	71,9

approx.	95°	Shore	Α
---------	-----	-------	---

Recommended Pretension	35%
Coeff. of friction μ steel approx.	0,45
Coeff. of friction μ PE approx.	0,25
Coeff. of friction μ HDPE approx.	0,2
FDA/EC compliant	

Characteristics



Hydrolysis resistance Hydrolysis resistance (HY). Suitable for humid environments.



microbial resistant Microbial resistant materials do not provide a breeding ground for microorganisms.



Cold-flexibleParticularly flexible at low temperatures down to -30°C



FDA (Food and Drug Administration) FDA/EC conformity for direct food contact

The above information is the result of in-house quality testing. They do not contain any guarantee of properties and in particular do not contain any statements about the suitability of the product for specific purposes, so that no claims against us can be derived from them. In particular, the information does not release the purchaser from his obligation to inspect incoming goods.

Subject to change without notice - 04/2025