

T-Profiles

PU65A ultramarine blue smooth



Article no.	Dimensions	Cross section cm ²	approx. weight kg/100m	Standard roll		Recommended min. pulley ØØ		Fmax/belt (standard)	
	mm			m	ft	mm	inch	kg	lbs
FBTG15X5LG	15x5	0,44	5,3	50	164	30	1,2	8,1	17,8

approx. 72° Shore A

Recommended Pretension 4...8%

Coeff. of friction μ steel approx. 0,8

Coeff. of friction μ PE approx. 0,5

Coeff. of friction μ HDPE approx. 0,45

FDA/EC compliant

Characteristics



Hydrolysis resistance
Hydrolysis resistance (HY). Suitable for humid environments.



Microbe resistant
Microbe-resistant materials do not provide a breeding ground for microorganisms.



FDA (Food and Drug Administration)
FDA/EC conformity for direct food contact

The above information is the result of in-house quality testing. They do not contain any guarantee of properties and in particular do not contain any statements about the suitability of the product for specific purposes, so that no claims against us can be derived from them. In particular, the information does not release the purchaser from his obligation to inspect incoming goods.

Subject to change without notice - 08/2024